

## Electronic Supplementary Information

### **Nanocrystalline alumina-supported ceria–praseodymia solid solutions: Structural characteristics and catalytic CO oxidation**

**Damma Devaiah,<sup>a,b</sup> Gode Thrimurthulu,<sup>a</sup> Panagiotis G. Smirniotis,<sup>b</sup> Benjaram M. Reddy<sup>a,\*</sup>**


*<sup>a</sup>Inorganic and Physical Chemistry Division, CSIR-Indian Institute of Chemical Technology, Uppal Road, Hyderabad – 500007, India*

*<sup>b</sup>Chemical Engineering Program, Biomedical, Chemical, and Environmental Engineering, University of Cincinnati, Cincinnati, OH 45221–0012, USA*

**Table S1.** The chemical composition of CP/A samples calcined at different temperatures

Sample	Nominal composition			Elemental composition from ICP-OES analysis		
	Ce	Pr	Al	Ce	Pr	Al
CP/A 773	0.80	0.20	1.00	0.79	0.21	0.99
CP/A 873	0.80	0.20	1.00	0.79	0.21	0.99
CP/A 973	0.80	0.20	1.00	0.78	0.22	0.99
CP/A 1073	0.80	0.20	1.00	0.78	0.22	0.99

**Fig. S1.** Cycling test of CP/A 773 for CO oxidation



**Fig. S2.** UV Raman spectra of spent CP/A 773 sample

