

Electronic Supplementary Information

Self-organized graphene-like boron nitride containing nanoflakes on copper by low-temperature N₂+H₂ plasma

B. B. Wang^a, D. Gao^b, I. Levchenko^c, K. Ostrikov^d, M. Keidar^e, M. K. Zhu^f, K. Zheng^b and B. Gao^g

-
- ^a. *College of Chemistry and Chemical Engineering, Chongqing University of Technology, 69 Hongguang Rd, Lijiatio, Banan District, Chongqing 400054, P. R. China.*
- ^b. *Institute of Microstructure and Properties of Advanced Materials, Beijing University of Technology, Beijing 100124, P. R. China.*
- ^c. *School of Chemistry, Physics and Mechanical Engineering, Queensland University of Technology, Brisbane QLD 4000, Australia. E-mail: Igor.Levchenko@qut.edu.au.*
- ^d. *Institute for Future Environments and School of Chemistry, Physics and Mechanical Engineering, Queensland University of Technology, Brisbane QLD 4000, Australia; CSIRO-QUT Joint Sustainable Materials and Devices Laboratory, Commonwealth Scientific and Industrial Research Organization, P.O. Box 218, Lindfield NSW 2070, Australia; Plasma Nanoscience, School of Physics, The University of Sydney, Sydney NSW 2006, Australia.*
- ^e. *Mechanical and Aerospace Engineering, The George Washington University, Washington DC 20052, USA.*
- ^f. *College of Materials Science and Engineering, Beijing University of Technology, Beijing 100124, P. R. China.*
- ^g. *College of Computer Science, Chongqing University, Chongqing 400044, P. R. China; Chongqing Municipal Education Examinations Authority, Chongqing 401147, China*




Fig. S1 FESEM images of the two samples with successfully synthesised two-dimensional BNCO nanoflakes. The growth durations was 20 min.




Fig. S2 Section FESEM images of samples A and B

Fig. S2 shows the section FESEM images of samples A and B. From Fig. S2 we have obtained the average thicknesses of films, which are about 172 and 284 nm for samples A and B, respectively.