

Electronic Supplementary Material (ESI) for RSC Advances.
This journal is © The Royal Society of Chemistry 2017

Electronic Supplementary Information

Highly Oriented Lamellar Polyaniline Films via Electrochemical Polymerization and Post-Growth Annealing

Suna Fan,^{a,b} Renwei Liu,^{a,b} Weitao Zheng^{*a} and Ming Li^{*b}

^a Key Laboratory of Automobile Materials of MOE, State Key Laboratory of Automotive Simulation and Control, and Department of Materials Science, Jilin University, Changchun, Jilin 130000, China.

^b Beijing National Laboratory for Condensed Matter Physics, Institute of Physics and School of Physical Sciences, University of Chinese Academy of Sciences, Beijing 100190, China
Chinese Academy of Sciences, Beijing, China

*Corresponding authors: mingli@iphy.ac.cn or wtzheng@jlu.edu.cn

DSC thermogram: Fig. S11 shows the DSC thermogram of the as-prepared PANI film. It exhibits the first endothermic peaks between 70~120 °C, which could be assigned to the release of water. The second endothermic transition observed between 170~200 °C is attributed to the loss of low-molecular-weight oligomers and dopant, which is consistent with the TGA result shown in Fig. 5.




Figure S11. DSC thermogram of the as-prepared PANI film.