### Supplementary Information:

# Surface analysis of curved polymeric plates irradiated with proton

## and ion beam

Young Seok Song<sup>a</sup>, Chul Kang<sup>a</sup>, Jiwon Jeong<sup>a</sup>, Minji Kim<sup>b</sup>, Eunju Lim<sup>b\*</sup>

<sup>a</sup>Department of Fiber System Engineering, Dankook University, Yongin 448-701, Korea <sup>b</sup>Department of Science Education/ Creative Convergence Manufacturing Engineering, Dankook University, Yongin 448-701, Korea

\* Corresponding author: Eunju Lim Tel.: +82-31-8005-3217; E-mail: elim@dankook.ac.kr

### 1. Material and experiment

Figure S1 shows the molecular structure of polycarbonate used in this study.



Fig. S1. Molecular structure of polycarbonate.

Figure S2 presents a schematic illustration of treatment with proton and nitrogen ion beams.



Fig. S2. Schematic illustration of treatment with proton and nitrogen ion beams.

#### 2. Results

The following tables present the glass transition temperature of the samples prepared in this study.

Tg[°C] of PC with Proton beam						
None	10 <sup>11</sup>	10 <sup>12</sup>	10 <sup>13</sup>	10 <sup>14</sup>		
138.5	138	137.5	138	124.5		

Tg[°C] of PC with Nitrogen ion beam						
None	10 <sup>14</sup>	10 <sup>15</sup>	10 <sup>16</sup>	10 <sup>17</sup>		
138.5	137.46	135.98	135. <mark>8</mark> 8	136.76		