

## Supporting Information

### An effective route for manufacturing the mushroom-derived carbon/SnO<sub>2</sub>/C functional composite

Qigang Han<sup>a, b</sup>, Yao Li<sup>a</sup>, Zhiwu Han<sup>c\*</sup>, Wenqiang Zhang<sup>a</sup>, Xiang Li<sup>a</sup>, Di Geng<sup>a</sup>, Xu Zhang<sup>a</sup>

<sup>a</sup> Roll Forging Research Institute, School of Materials Science and Engineering, Jilin University, Changchun 130022, P. R. China

<sup>b</sup> State Key Laboratory of Automotive Simulation and Control, Jilin University, Changchun 130022, P. R. China

<sup>c</sup> Key Laboratory of Bionic Engineering (Ministry of Education), Jilin University, Changchun 130022, Jilin, P. R. China

\* Corresponding author.

E-mail address: [zwhan@jlu.edu.cn](mailto:zwhan@jlu.edu.cn) (Zhiwu Han). Tel. / fax: +86 431 85094340




Fig. S1. The XPS results of MC survey scan.




Fig. S2. EIS plots of MC, MC/SnO<sub>2</sub>-FC and MC/SnO<sub>2</sub>/C-FC.

Table S1. Elemental compositions and the content (at. %) of MC and MC/SnO<sub>2</sub>/C-FC.

Sample	Element	Content (at. %)
MC	C 1s	75.51
	O 1s	14.47
	N 1s	6.79
	Si 2p	2.07
	P 2p	1.16
MC/SnO <sub>2</sub> /C-FC	C 1s	68.31
	O 1s	24.51
	Sn 3d	7.18