


Supporting data 2

DC measurements results



Results of DC measurements of 10- and 5-layered LB films after the photo-modification where the AC plots stayed constant. The Ohmic current was obtained in the 0-10 voltage region. The resistivity of $69 \text{ M}\Omega$ (10-layered LB film) and $125 \text{ M}\Omega$ (5-layered LB films) coincided well with the R components in the AC measurements.