

Supplemental Information

Selective oxidation of cyclohexane over gold nanoparticles supported on mesoporous silica prepared in the presence of thioether functionality

Pingping Wu ^{a, b}, Zhigang Xiong ^a, Kian Ping Loh ^{b, c}, X. S. Zhao ^{a, b*}

Table S1 Cyclohexane oxidation results on different gold catalysts

Catalyst ^{reference}	Oxidant/ MPa	Temperature (K)	Reaction time (h)	Conversion (mol.%)	K/A oil Selectivity (mol.%)	TOF (h ⁻¹)
Au/ ZSM-5 ¹	O ₂ /1.0	423	4	16.0	92.0	2242
Au/MCM-41 ²	O ₂ /1.0	423	6	19.0	94.0	1907
Au/Al ₂ O ₃ ³	O ₂ /1.5	423	3	12.6	88.0	16136
Au/APS-SBA-15 ⁴	O ₂ /1.5	423	6	21.0	96.0	661
Au/SH-SBA-15 ⁴	O ₂ /1.5	423	6	32.0	94.0	858
Au/TiO ₂ /SiO ₂ ⁵	O ₂ /1.0	423	3	8.4	91.7	40133

References:

1. R. Zhao, D. Ji, G. M. Lv, G. Qian, L. Yan, X. L. Wang and J. S. Suo, *Chem. Commun.*, 2004, 904-905.
2. G. M. Lu, R. Zhao, G. Qian, Y. X. Qi, X. L. Wang and J. S. Suo, *Catal. Lett.*, 2004, **97**, 115-118.
3. L. X. Xu, C. H. He, M. Q. Zhu and S. Fang, *Catal. Lett.*, 2007, **114**, 202-205.
4. K. K. Zhu, J. C. Hu and R. Richards, *Catal. Lett.*, 2005, **100**, 195-199.
5. L. X. Xu, C. H. He, M. Q. Zhu, K. J. Wu and Y. L. Lai, *Catal. Lett.*, 2007, **118**, 248-253.