## **Supplementary information**

## Formation of highly elastomeric and property-tailorable poly(glycerol sebacate)-co-poly(ethylene glycol) hydrogels through thiol-norbornene photochemistry

Yu-Ting Tsai,<sup>a</sup> Chun-Wei Chang<sup>a</sup> and Yi-Cheun Yeh<sup>\*a</sup>

<sup>a</sup> Institute of Polymer Science and Engineering, National Taiwan University, Taipei, Taiwan

E-mail: yicheun@ntu.edu.tw



**Fig. S1** GPC traces of PGS-co-PEG and Nor\_PGS-*co*-PEG macromers. PGS-*co*-PEG: Mw= 8.8 kDa, PDI= 6.87; Nor\_PGS-*co*-PEG: Mw= 9.6 kDa, PDI= 2.71.