

Table S1

Entry	Catalyst	Pd loading, %	T (°C)	Conversion, %	Selectivity, %	Reference
1	Pd/Al ₂ O ₃	3	130	100	26	Huang et.al ¹
2	Pd/Ni(OH) ₂		105	80	80	Hu et.al ²
3	Pd/ZnO SAC	1	80	>99	80	Zhou et.al ³
4	Pd ₄ S		50	100	60	Liu et.al ⁴
5	Pd ₂ F/ fiberglass		370	51	100	Gulyaeva et.al ⁵
6	PdP ₂ /TiO ₂	2	225	>99	82	Liu et.al ⁶
7	AgPd/SiO ₂	0.5	240-280	> 99	60-90	Pei et.al ⁷
8	PdZn		60	>90	100	Shao et.al ⁸
9	Pd/Cu(111)		225	100	85	Liu et.al ⁶
10	Pd-Ag/Mg-Ti	1	70	>99	>99	Liu et.al ⁹
11	PdLa/N-pgBC	0.25(Pd/La=1)	240	100	>94.2	This work




Fig. S1. TG(a), XRD(b), and TEM images(c) of the spent catalyst.

References:

1. X. Huang, Y. Xia, Y. Cao, X. Zheng, H. Pan, J. Zhu, C. Ma, H. Wang, J. Li and R. You, *Nano Research*, 2017, 10, 1-11.
2. M. Hu, J. Zhang, W. Zhu, Z. Chen, X. Gao, X. Du, J. Wan, K. Zhou, C. Chen and Y. Li, *Nano Research*, 2018, 11, 905-912.
3. Huiran, Zhou, Xiaofeng, Yang, Aiqin, Wang, Shu, Miao, Xiaoyan and Liu, *Chinese Journal of Catalysis*, 2016.
4. L. Yanan, A. J. Mccue, F. Junting, G. Shaoliang, L. Dianqing and J. A. Anderson, *Journal of Catalysis*, 2018, 364, 204-215.
5. Y. K. Gulyaeva, V. V. Kaichev, V. I. Zaikovskii, E. V. Kovalyov, A. P. Suknev and B. S. Bal'zhinimaev, *Catalysis Today*, 2015, 245, 139-146.
6. L. Yanan, A. J. Mccue, M. Chenglin, F. Junting, L. Dianqing and J. A. Anderson, *Journal of Catalysis*, 2018, 364, 406-414.
7. G. X. Pei, X. Y. Liu, A. Wang, A. F. Lee, M. A. Isaacs, L. Li, X. Pan, X. Yang, X. Wang, Z. Tai, K. Wilson and T. Zhang, *Acs Catalysis*, 2015, 5, 3717-3725.
8. H. Zhou, X. Yang, L. Li, X. Liu, Y. Huang, X. Pan, A. Wang, J. Li and T. Zhang, *Acs Catalysis*, 2016.
9. Y. Liu, J. Zhao, Y. He, J. Feng, T. Wu and D. Li, *Journal of Catalysis*, 2017, 348, 135-145.