

Supplementary Information

Influence of interstitial UO_2^{2+} doping on the valence control of Eu and energy transfer to substitutional Eu^{3+} and Sm^{3+} in SrBPO_5

P. Vinodkumar^{ab}, R. K. Padhi^{b*}, Sitakanta Panda^{ab}, P. Ramakrishna^{ac} and B. S. Panigrahi^{ab}

^a Homi Bhabha National Institute, Kalpakkam, Tamil Nadu, India, 603102.

^b Indira Gandhi Centre for Atomic Research, Kalpakkam, Tamil Nadu, 603102.

^c Safety Research Institute, AERB, Kalpakkam, 603102

* Corresponding author: email id: rangibkumarpadhi@gmail.com; ranjib@igcar.gov.in

Table S1.

Table S1: Sm^{2+} transitions and corresponding emission maxima in $\text{SBP:Sm}_{0.005}$

Transition	$^5\text{D}_0 \rightarrow ^7\text{F}_0$	$^5\text{D}_0 \rightarrow ^7\text{F}_1$	$^5\text{D}_0 \rightarrow ^7\text{F}_2$	$^5\text{D}_0 \rightarrow ^7\text{F}_3$	$^5\text{D}_0 \rightarrow ^7\text{F}_4$
Emission maxima, nm (cm^{-1})	678 (14749) 683 (14641)	688 (14535) 691 (14472) 695 (14388) 703 (14225) 709 (14104)	718 (13928) 723 (13831) 727 (13755) 732 (13661) 734 (13624) 737 (13568) 744 (13441)	757 (13210) 765 (13072) 767 (13038) 770 (12987)	805 (12422) 813 (12300) 819 (12210) 823 (12151)