Electronic Supplementary Material (ESI) for New Journal of Chemistry.

This journal is © The Royal Society of Chemistry and the Centre National de la Recherche Scientifique 2021

Electronic Supporting Information for:

Oleophobic Composite Films Based on Multi-Layer Graphitic Scaffolding

Rachel L. McLaren, Rosenildo C. da Costa, Christian J. Laycock, David J. Morgan, Michael E.A. Warwick and Gareth R. Owen*

Table of Contents

A. Free-Standing Film Preparation (Page 2)

Figure S1 – Photographs of free-standing film preparation: (a) deposition of a dispersion of MLG-PP in methanol into eight sections of a tray; (b) solvent evaporation in air to form films at the bottom of each section and (c) an isolated free-standing film.

B. XPS Analysis (Page 2)

Figure S2 - Deconvoluted spectrum of C 1s orbital for MLG-PP composite.

C. Additional SEM Images (Page 3)

Figure S3 – SEM images of MLG-PP film at magnifications of (a) 414 x (b) 2.07 kx (c) 4.17 kx (d) 10.45 kx and (e) 34.56 kx.

Figure S4 – SEM image of MLG-PP film depicting the thickness at a magnification of 198 x.

D. Contact Angle Measurements (Page 4)

Figure S5 — Contact angle measurements (°) for silicone oil, hexadecane and Jet A-1 fuel on MLG-PP film with photographs of the droplet in each case.

A. Free-Standing Film Preparation




Figure S1 – Photographs of free-standing film preparation: (a) deposition of a dispersion of MLG-PP in methanol into eight sections of a tray; (b) solvent evaporation in air to form films at the bottom of each section and (c) an isolated free-standing film.

B. XPS Analysis




Figure S2 - Deconvoluted spectrum of C 1s orbital for MLG-PP composite.

C. Additional SEM Images




Figure S3 – SEM images of MLG-PP film at magnifications of (a) 414 x (b) 2.07 kx (c) 4.17 kx (d) 10.45 kx and (e) 34.56 kx.




Figure S4 – SEM image of MLG-PP film depicting the thickness at a magnification of 198 x.

D. Contact Angle Measurements

Silicone Oil	Hexadecane	Jet A-1 Fuel
105.9	126.4	111.9

Figure S5 – Contact angle measurements (°) for silicone oil, hexadecane and Jet A-1 fuel on MLG-PP film with photographs of the droplet in each case.