

1

Supplementary Information

2 **Tuning Brønsted and Lewis Acidity on Phosphated Titanium Dioxides**

3 **for Efficient Conversion of Glucose to 5-hydroxymethylfurfural**

4 Siripit Songtawee,^{ab} Bunyarat Rungtaweavoranit,^a Chalida Klaysom,^{bc}

5 and Kajornsak Faungnawakij ^{*a}

6 *^a NanoCatalysis and Molecular Simulation Research Group, National Nanotechnology*

7 *Center (NANOTEC), National Science and Technology Development Agency (NSTDA),*

8 *Pathumthani 12120, Thailand*

9 *^b Center of Excellence in Particle and Material Processing Technology, Department of*

10 *Chemical Engineering, Faculty of Engineering, Chulalongkorn University, Bangkok,*

11 *Thailand*

12 *^c Bio-Circular-Green Economy Technology & Engineering Center (BCGeTEC), Department*

13 *of Chemical Engineering, Faculty of Engineering, Chulalongkorn University, Bangkok,*

14 *Thailand*

15 ** Corresponding author: Tel.: +66 2 564 7100, Fax: +66 2 564 6981,*

16 *E-mail address: kajornsak@nanotec.or.th*

17


18

19

20

21

22



23 **Fig. S1** The μ -EDXRF spectra of (a) fresh and (b) spent of 30P-TiO₂ catalyst

24

25 **Table S1** The elemental analysis of fresh and spent of 30P-TiO₂ catalysts by μ -EDXRF

Element (%)	Fresh 30P-TiO ₂	Spent 30P-TiO ₂
P	15.2	12.6
Ti	84.8	80.1
Na	-	5.7

26

27