

Supplementary Materials

Effect of surface properties of TiO₂ on the performance of Pt/TiO₂ catalysts for furfural hydrogenation

Mi Yeon Byun ^{a,b}, Ye Eun Kim ^{a,d}, Jae Ho Baek ^a, Jungho Jae ^{c+}, and
Man Sig Lee ^{a,e+}

^a Ulsan Division, Korea Institute of Industrial Technology (KITECH), Ulsan 44413,
Republic of Korea

^b Department of Polymer Science and Chemical Engineering, Pusan National University,
Busan 46241, Republic of Korea

^c School of Chemical Engineering, Pusan National University, Busan 46241, Republic
of Korea

^d Department of Chemical and Biological Engineering, Korea University, Seoul 02841,
Republic of Korea

^e Department of Green Process and System Engineering, University of Science and
Technology (UST), Ulsan 44413, South Korea

⁺Correspondence: Tel: +82-52-980-6630, Fax: +82-52-980-6639,

E-mail: lms5440@kitech.re.kr (M.S. Lee)

Correspondence: Tel: +82-51-510-2989,

E-mail: jh.jae@pusan.ac.kr (J. Jae)

Table captions

Table S1. Comparison of furfural hydrogenation over various catalysts

Table S1. Comparison of furfural hydrogenation over various catalysts

Catalysts	Furfural (mmol)	Solvent	Temp. (°C)	Pressure (bar)	Time (h)	Conversion (%)	CPO Yield (%)	Ref..
Pt/C	11	Water	160	80	1	100	76	1
Cu/ZnAl-500	5	Water	150	40	6		62	2
Ni/TiO ₂ -450	1	Water	140	10	6	74.7	65.6	3
Pd/UiO-66-NO ₂	1.04	Water	150	10	5	98.9	96.6	4
Pt/NC-BS-800	2.5	Water	150	30	4	>99	76.0	5
Pt/TiO ₂ NR	26	Water	170	20	2	98	49.4	This work

References)

1. M. Hronec and K. Fulajtarova, “Selective transformation of furfural to cyclopentanone”, *Catal. Comm.* 24 (2012) 100-104.
2. J. Gao et al. “Selective conversion of furfural to cyclopentanone with CuZnAl catalysts”, *ACS Sustain. Chem. Eng.* 2 (2014) 2259-2266.
3. S. Chen et al. “Hydrogenation of furfural to cyclopentanone under mild conditions by a structure-optimized Ni-NiO/TiO₂ heterojunction catalyst”, *ChemSusChem* 13 (2020) 5507-5515.
4. C. Wang et al. “Hydrogenative ring-rearrangement of furfural to cyclopentanone over Pd/UiO-66-NO₂ with tunable missing-linker defects”, *Molecules* 26 (2021) 5736.
5. X. Liu et al.” Tunable and selective hydrogenation of furfural to furfuryl alcohol and cyclopentanone over Pt supported on biomass-derived porous heteroatom doped carbon”, *Faraday Discussions* 202 (2017) 79-98.