

Supplementary Material

pH-responsive curcumin-based nanoscale ZIF-8 combining chemophotodynamic therapy for excellent antibacterial activity

Xiaofeng Meng^{a,b,#}, Jingwei Guan^{a,b,#}, Shanshan Lai^{a,b}, Liming Fang^{c,e,f,*},

Jianyu Su^{a,b,c,d,*}

^a *School of Food Science and Engineering, South China University of Technology, Guangzhou 510640, Guangdong, China*

^b *Guangdong Province Key Laboratory for Green Processing of Natural Products and Product Safety, Guangzhou, 510640, Guangdong, China.*

^c *Sino-Singapore International Joint Research Institute, Guangzhou 510700, Guangdong, China.*

^d *Overseas Expertise Introduction Center for Discipline Innovation of Food Nutrition and Human Health (111 Center), Guangzhou 510640, Guangdong, China.*

^e *Key Laboratory of Biomedical Engineering of Guangdong Province, School of Materials Science and Engineering, South China University of Technology, Guangzhou 510640, China.*

^f *National Engineering Research Center for Tissue Restoration and Reconstruction, South China University of Technology, Guangzhou 510006, China.*

^g *College of Food Science, South China Agricultural University, Guangzhou 510642, Guangdong, China*

* Corresponding author.

E-mail addresses: jysu@scut.edu.cn (Jianyu Su), lmfang@scut.edu.cn (Liming Fang)

These authors contributed equally to this work.

Table S1 Synthesis of CCM@ZIF

Entry	Zn(NO ₃) ₂ ·6H ₂ O (mg)	2-MIM (mg)	CCM (mg)	Time (min)	DLC (%)	DLE (%)
1	150	330	3	15	2.23	13.02
2	150	330	5	15	7.15	43.79
3	150	330	9	15	6.31	21.58
4	150	330	15	15	6.28	12.94
5	150	330	25	15	31.60	57.76
6	150	330	5	5	11.57	82.76
7	150	330	5	10	2.47	21.96
8	150	330	5	20	8.37	48.42




Fig. S1 (A) The UV-vis absorption of CCM in ethanol. (B) The linear relationship between the concentration of CCM in ethanol and absorption intensity, and the regression equation is $y = 0.1521x + 0.0401$ ($R^2 = 0.9982$).