

Supporting Information

IL-functionalized Mn(II) -doped core-shell Fe₃O₄@ Zr-MOF nanomaterials for removal MB from wastewater based on dual adsorption/Fenton catalysis

Ruowei Lu,^a Cuijuan Wang,^a *Yanxia Chen,^a Lichuan Tan,^a Peng Wang,^a and Siwen Feng^a

^a Department of Chemistry and Chemical Engineering, School of Life Science and Engineering, Southwest Jiaotong University, Chengdu, Sichuan, 610031, PR China

*Corresponding Author

Figures and tables




Figure. S1. (a) PXRD patterns and (b) FT-IR spectra of NH₂-UiO-66.




Figure. S2. EDS spectrum of the obtained MFC@Mn-NH₂-UiO-66 and MFC@Mn-NH₂-UiO-66@IL magnetic composites.




Figure. S3. XPS spectra of MFC@Mn-NH₂-UiO-66@IL.




Figure. S4. (a) SEM and (b) TEM images of $\text{NH}_2\text{-UiO-66}$.




Figure. S5. The pore size distribution of $\text{NH}_2\text{-UiO-66}$, $\text{MFC@Mn-NH}_2\text{-UiO-66}$ and $\text{MFC@Mn-NH}_2\text{-UiO-66@IL}$ nanocomposites.




Figure. S6. (a) Kinetics plot of the pseudo first-order, and (b) intra-particle diffusion kinetic model for MB adsorption.




Figure. S7. Adsorption isotherm of (a) Langmuir, and (b) Freundlich model for MB removal by MFC@Mn-NH₂-UiO-66@IL.




Figure. S8. Before and after comparison of adsorption/catalytic MB.




Figure. S9. Recycle efficiency of MFC@Mn-NH₂-UiO-66@IL over three cycles.




Figure. S10. (a)FT-IR spectra and (b)PXRD patterns MFC@Mn-NH₂-UiO-66@IL composite before and after adsorption of MB.




Figure. S11. XPS spectra of the recycled MFC@Mn-NH₂-UiO-66@IL: (a) The survey spectrum; (b) XPS Zr 3d spectrum.

Table. S1. Element components of MFC@Mn-NH₂-UiO-66, and MFC@Mn-NH₂-UiO-66@IL.

Samples	C (wt%)	Zr (wt%)	O (wt%)	F (wt%)	Fe (wt%)	N (wt%)	P (wt%)	Mn (wt%)
MFC@Mn-NH ₂ -UiO-66	41.51	24.46	15.95	-	11.4	4.07	-	1.05
IL@MFC@Mn-NH ₂ -UiO-66	31.21	23.28	21.62	7.68	6.41	7.44	1.53	0.66

Table. S2. BET surface areas and t-plot micropore volumes of samples.

Samples	$S_{BET}(m^2 \cdot g^{-1})$	$V_{pore}(cm^3 \cdot g^{-1})$
NH ₂ -UiO-66	1264.30	0.54
MFC@Mn-NH ₂ -UiO-66	699.25	0.46
MFC@Mn-NH ₂ -UiO-66@IL	30.31	0.06

Table. S3. Intra-particle diffusion model parameters for the adsorption of MB dye onto MFC@Mn-NH₂-UiO-66@IL composite

$C_0(mg \cdot L^{-1})$	First step			Second step			Third step		
	$K_{id, 1}$ (mg g ⁻¹ min ^{-0.5})	C_1 (mg · L ⁻¹)	R^2	$K_{id, 2}$ (mg g ⁻¹ min ^{-0.5})	C_2 (mg · L ⁻¹)	R^2	$K_{id, 3}$ (mg g ⁻¹ min ^{-0.5})	C_3 (mg · L ⁻¹)	R^2
50 mg · L ⁻¹	57.69	-76.25	0.98	6.09	196.86	0.67	1.58	156.48	0.94
100 mg · L ⁻¹	36.72	-48.33	0.98	0.51	116.35	0.88	0.25	112.72	0.98

Table. S4. R_L values for the adsorption of MB dye.

$C_0(mg \cdot L^{-1})$	10	20	40	60	80	100	150	200
R_L	0.20	0.11	0.06	0.04	0.03	0.025	0.016	0.012