

## Supplementary materials

### Contents

**Table S1** Materials particle sizes

**Figure S1** Zeta potential of materials. (A) PEI-M (B) PEG-M (C) PVP-M (D)PEI-N (E)PEG-N (F) PVP-N.


**Figure S2** H9C2 viability test by (A) MTT assay and (B) LDH assay in N-AuNCs group.

**Figure S3** Representative microscopy images of primary cardiomyocytes incubated with AuNCs and palmitate acid for 24 h. The cardiomyocytes were stained by mitotracker red and green DCFH-DA (scale bar: 100  $\mu$ m).


**Figure S4** (A) JC-1 and (B) ROS fluorescence staining in H9C2 cells treated with AuNCs, M-AuNCs, and N-AuNCs.

**Table S1** Materials particle sizes


Materials	Size (nm)	St Dev(nm)
PEI-M	8.768	0.910
PEG-M	3.635	0.377
PVP-M	1.155	0.138
PEI-N	6.377	1.306
PEG-N	35.370	6.800
PVP-N	12.44	2.132




**Figure S1** Zeta potential of materials. (A) PEI-M (B) PEG-M (C) PVP-M (D)PEI-N (E)PEG-N (F) PVP-N.



**Figure S2** H9C2 viability test by (A) MTT assay and (B) LDH assay in N-AuNCs group.



**Figure S3** Representative microscopy images of primary cardiomyocytes incubated with AuNCs and palmitate acid for 24 h. The cardiomyocytes were stained by mitotracker red and green DCFH-DA (scale bar: 100  $\mu$ m).



**Figure S4** (A) JC-1 and (B) ROS fluorescence staining in H9C2 cells treated with AuNCs, M-AuNCs, and N-AuNCs.