

High Mass Loading Flexible Electrode with Sheet-like $\text{Mn}_3\text{O}_4/\text{NiMoO}_4@\text{NiCo}$ LDH on Carbon Cloth for supercapacitor

Ruibin Liang^{‡a}, Si Liu^{‡a}, Jianrong Lin^a, Jingfei Dai^a, Jingyi Peng^a, Peiyuan Huang^a, Jianwen Chen^b,

Peng Xiao^{a*}

^a Guangdong-Hong Kong-Macao Joint Laboratory for Intelligent Micro-Nano Optoelectronic Technology, School of Physics and Optoelectronic Engineering, Foshan University, Foshan 528225, China ;

^b School of Electronic and Information Engineering, Foshan University, Foshan, 528000, China

*Correspondence: xiaopeng@fosu.edu.cn.

[‡] These authors contributed equally to this work.

Supplementary data




Figure S1 XPS spectrum of the MO/NMO/NiCo LDH




Figure S2 curves of MO/NMO/NiCo LDH with different mass loading (a) CV; (b) GCD




Figure S3 error bars of the specific capacitance of MO/NMO/NiCo LDH at different current density




Figure S4 (a) CV curves of the FSC at 50 mV/s with different potential window; (b) GCD curves of the FSC at different bending condition; (d) EIS curves of the FSC at different bending condition

Table S1 CV curve area of each status at the scan rate of 50 mV/s

	Original status	Folded 200 times	Folded 300 times	Folded 400 times	Folded 500 times	Folded 600 times
CV curve area	3.768	2.509	2.487	2.525	2.576	2.543