

Table S1. Proficiency testing results of toys in laboratory performance assessment

Analyte	PVC folium adopted – mean value (Check 2016) % (w/w)	Laboratory of Institute of Public Health of Serbia % (w/w)	Rubber material adopted – mean value (LGC 2017) % (w/w)	Laboratory of Institute of Public Health of Serbia % (w/w)	Combined material adopted – mean value (LGC 2021) % (w/w)	Laboratory of Institute of Public Health of Serbia % (w/w)
BBP	18.80 ± 2.82	19.40	/	/	0.15 ± 0.03	0.17
DBP	27.30 ± 4.10	27.30	/	/	0.12 ± 0.03	0.14
DEHP	29.60 ± 4.44	29.50	/	/	0.14 ± 0.03	0.13
DNOP	24.30 ± 3.64	21.10	/	/	0.07 ± 0.02	0.06
DIBP	/	/	/	/	0.21 ± 0.03	0.23
DINP	33.50 ± 8.37	25.90	22.74 ± 5.49	24.91	0.19 ± 0.06	0.15
DIDP	15.20 ± 3.77	11.46	2.65 ± 0.77	2.12	0.24 ± 0.03	0.19