

Electronic supplementary information (ESI):

Self-assembled hollow CuS@AuNRs/PDA nanohybrids with synergistically enhanced photothermal efficiency

Chiyin Zhang,^{a,b} Panping Yang,^{a,b} Jingguo Li,^c Shaokui Cao,^{a,b} Yingliang Liu^{a,b} and Jun Shi^{a,b*}

^a *School of Materials Science and Engineering, Zhengzhou University, Zhengzhou 450001, China.*

^b *Henan Key Laboratory of Advanced Nylon Materials and Application, Zhengzhou University, Zhengzhou 450001, People's Republic of China.*

^c *People's Hospital of Zhengzhou University, Zhengzhou University, Zhengzhou 450003, China.*

* Address correspondence to E-mail: shijun@zzu.edu.cn

Figure Captions:

Figure S1. Average hydrodynamic diameters of hollow CuS measured using dynamic light scattering.

Figure S2. Digital photographs of HCuS@AuNRs in different media (100 µg/mL, deionized water on the left and PBS pH 7.4 on the right).

Figure S3. Linear fitting curves of $\ln(M_t/M_\infty)$ versus $\ln t$ of HCuS@AuNRs/PDA (A) at different pH values without laser irradiation, (B) at pH 4.5 upon different laser irradiation (1.6 W/cm² and 0 W/cm²).

Figure S4. (A) Cytotoxicity evaluation to EA.hy926 cells of HCuS@AuNRs/PDA at pH 7.4, (B) Cytotoxicity evaluation (MCF-7 cells) of HCuS@AuNRs/PDA-DOX at pH 7.4 with or without NIR irradiation.

Table S1. TEM-EDS element mass percentage of HCuS@AuNRs/PDA.

Table S2. Parameters k , n and R^2 for the DOX release of HCuS@AuNRs/PDA at different release conditions.




Figure S1. Average hydrodynamic diameters of hollow CuS measured using dynamic light scattering.




Figure S2. Digital photographs of HCuS@AuNRs in different media (100 µg/mL, deionized water on the left and PBS pH 7.4 on the right).




Figure S3. Linear fitting curves of $\ln (M_t/M_\infty)$ versus $\ln t$ of HCuS@AuNRs/PDA (A) at different pH values without laser irradiation, (B) at pH 4.5 upon different laser irradiation (1.6 W/cm² and 0 W/cm²).




Figure S4. (A) Cytotoxicity evaluation to EA.hy926 cells of HCuS@AuNRs/PDA at pH 7.4, (B) Cytotoxicity evaluation (MCF-7 cells) of HCuS@AuNRs/PDA-DOX at pH 7.4 with or without NIR irradiation.

Table S1 TEM-EDS element mass percentage of HCuS@AuNRs/PDA.

Elements	Cu	S	Au	N	C
Mass percentage (%)	22.45	7.92	8.61	2.68	58.34

Table S2 Parameters k , n and R^2 for the DOX release of HCuS@AuNRs/PDA at different release conditions.

Sample	release conditions	k	n	R^2
HCuS@AuNRs/PDA	pH 7.4, 0 W/cm ²	2.7114×10^{-7}	1.0613	0.9786
HCuS@AuNRs/PDA	pH 6.0, 0 W/cm ²	0.9011×10^{-5}	0.4248	0.9642
HCuS@AuNRs/PDA	pH 4.5, 0 W/cm ²	1.14×10^{-3}	0.5444	0.9752
HCuS@AuNRs/PDA	pH 4.5, 1.6 W/cm ²	9.71×10^{-3}	0.3812	0.9601