

Supplementary Information

Cobalt-promoted Zn encapsulation within Silicalite-1 for oxidative propane dehydrogenation with CO₂ by microwave catalysis at low temperature

Fangui Nie^a, Hongyang Sun^a, Tianyi Li^a, Zhimin You^{b*}, Jicheng Zhou^{a,c}, Wentao Xu^{a,c,*}

a. Key Laboratory of Green Catalysis and Chemical Reaction Engineering of Hunan Province, School of Chemical Engineering, Xiangtan University, Xiangtan 411105, P.R.China

b. School of Environment and Resource, Xiangtan University, Xiangtan 411105, P.R.China


c. National and Local United Engineering Research Center for Chemical Process Simulation and Intensification, Xiangtan University, Xiangtan 411105, P.R.China

*Corresponding Author

Tel/fax: +86-731 58298173.

E-mail: wentaouxu@xtu.edu.cn (W. Xu); yzmxtu@163.com (Z. You)

1




2

3

4

5

Figure S1. Raman spectrum of Co@S-1 catalyst.



6

7

8

Figure S2. HRTEM images of Zn₈Co₁@S-1 catalyst.




Figure S3. Performance of propane dehydrogenation under microwave. (a) Zn₈Co₁/S-1+SiC and Co@S-1+SiC microwave catalysts; (b) effect of different amounts of Zn and Co substances on catalytic activity; (c) effect of diffusion within the Zn₈Co₁/S-1+SiC microwave catalyst; (d) effect of diffusion outside the Zn₈Co₁/S-1+SiC microwave catalyst; (e) CO₂ conversion over Zn₈Co₁@S-1 catalysts at MW and CH, respectively **Reaction conditions:** 0.5 g catalyst+3 g SiC, 400-550 °C, 20-80+ mesh, 20~100 mL/min total flow of 10 vol% C₃H₈ and 20 vol% CO₂ in Ar for CO₂-ODHP, microwave power: 450-800W




Figure S4. (a) Product distribution of $\text{Zn}_8\text{Co}_1@\text{S}-1$ catalyst at different temperatures under CH; (b) Linear fitting curves of CO_2 -ODHP for catalysts under MW and CH.

Reaction conditions: 0.5 g catalyst+3 g SiC, 400-580 °C, 40-60 mesh, 60 mL/min total flow of 10 vol% C_3H_8 and 20 vol% CO_2 in Ar for CO_2 -ODHP, microwave power: 450-800W




Figure S5. Photograph of $\text{Zn}_8\text{Co}_1@\text{S}-1$ catalyst. (a) Fresh catalyst; (b) Spent catalyst after PDH reaction; (c) Spent catalyst after CO_2 -ODHP reaction.