

## Supporting Information

### High comprehensive properties of colorless transparent polyimide films derived from fluorine-containing and ether-containing dianhydride

Yan Shi <sup>#a</sup>, Jinzhi Hu <sup>#a</sup>, Xiaomin Li <sup>a,b</sup>, Jing Jian <sup>a</sup>, Lili Jiang <sup>a</sup>, Chuanqiang Yin <sup>\* a,b</sup>,  
Yuchun Xi <sup>b</sup>, Kai Huang <sup>a</sup>, Liejun Su <sup>a</sup>, Lang Zhou <sup>a,b</sup>

<sup>a</sup> Institute of Photovoltaics, Nanchang University, Nanchang 330031, P.R. China

<sup>b</sup> Institute of New Materials Technology, NCU-GQC Institute of PV-HE-ES Technology, Jiujiang 332020, P.R. China

\*Corresponding author: cqyin@ncu.edu.cn (C. Yin)

# These two authors contributed equally to this paper.

Table S1 XRD data and Free Volume Fraction of CPI Films

Number	2 $\theta$ (°)	<i>d</i> (Å)	FFV
CPI-1	20.88	4.2494	0.2158
CPI-2	20.79	4.2682	0.2353
CPI-3	21.02	4.2215	0.2339
CPI-4	18.53	4.7829	0.2480
CPI-5	18.74	4.7290	0.2576
CPI-6	16.36	5.4126	0.2552

Table S2 The Molecular Orbital Energies of HOMO, LUMO, and energy band gaps of CPI films.

Number	BPADA	6FDA	6FDA loading (%)	$E_{\text{HUMO}}(\text{eV})$	$E_{\text{LUMO}}(\text{eV})$	$E_{\text{GAP}}(\text{eV})$
PI-1	3	0	0	-5.7786	-2.3155	3.4631
PI-2	2	1	33.33	-6.3762	-2.8565	3.5197
PI-3	1	2	66.67	-6.5209	-2.8549	3.6660
PI-4	0	3	100	-6.8001	-2.9049	3.8952




Fig. S1 Dielectric constants of CPI films from 1000 Hz to 10 MHz