



ZnO:Sb wire resistance versus time. IPA treatment causes the resistance to rise. Yet, turning the light on causes a larger drop in resistance compared to the untreated sample. So, the IPA treatment makes the sample surface more sensitive to light treatment.