

Supplementary Material (ESI) for Dalton Transactions

## Photo- and Electroluminescence in Thin Films of Covalently Bonded Azomethin-Zinc/SiO<sub>2</sub> Hybrid Materials

Chenyang Wei, Peng Jiang, Weimin Huang, Qianjun He, Xiangzhi Cui and Jianlin Shi\*

State Key Lab of High Performance Ceramics and Superfine Microstructure, Shanghai Institute of Ceramics,

Chinese Academy of Science, Shanghai 200050, People's Republic of China.

Fax: +86 21 5241 3122; E-mail: jlshi@sunm.shenc.ac.cn




Figure S1. The GC spectra of reaction solution




Figure S2. The mass spectra of SiAM




Figure S3. The photo image of the solution and the spin-coated film of SiAM-Zn.




Figure S4. X-ray diffraction pattern of the hybrid film of SiAM-Zn.




Figure S5. Schematic drawings of OLEDs.




Figure S6. The OLED device with SiAM-Zn as LEL in electroluminescent emission measurement.




Figure S7. Sectional SEM image of the OLED device.

Table S1. Electroluminous intensity vs voltage and current with SiAM-Zn as LEL.

Voltage (V)	8	10	12	14	16	18	20
Current (mA)	0.29	0.86	2.5	5.4	11	20	38
Luminous Intensity (Cd/m <sup>2</sup> )	0.075	0.327	0.585	0.737	1.287	1.979	2.539

Table S2. Voltage vs current with SiAM as LEL.

Voltage (V)	10	12	14	16	18	20
Current (mA)	0.18	0.19	0.26	0.35	0.45	0.55