## Electronic supplementary information (ESI) for Mesosilica-coated Ultrafine fibers for High Efficient Laccase Encapsulation

Shiwen Wang<sup>*a,b*</sup>, Wei Chen<sup>c</sup>, Sha He<sup>*b*</sup>, Qilong Zhao<sup>*b*</sup>, Xiaohong Li<sup>\*a</sup>, Jiashu Sun<sup>\*b</sup> and Xingyu Jiang<sup>\*b</sup>

<sup>a</sup> Key Laboratory of Advanced Technologies of Materials, Ministry of Education of China, School of Materials Science and Engineering, Southwest Jiaotong University, Chengdu 610031, China; E-mail: <u>xhli@swjtu.edu.cn</u>
<sup>b</sup> Beijing Engineering Research Center for BioNanotechnology & Key Lab for Biological Effects of Nanomaterials and Nanosafety, National Center for NanoScience and Technology, Beijing 100190, China; E-mail: <u>xingyujiang@nanoctr.cn</u>; <u>sunjs@nanoctr.cn</u>
<sup>c</sup> University of Groningen, Zernike Institute for Advanced Materials, Department of Polymer Chemistry, Nijenborgh 4, 9747 AG, Groningen, the Netherlands

† Electronic supplementary information (ESI) available.

Elements	Atomic percentage	
	Before	After
С	94.90	82.40
О	5.10	10.13
S	0	3.14
Si	0	3.13
N	0	1.21

 Table S1: The element analysis of PS ES fibers before silica modification (Before)

 and after silica modification (After).



Fig. S1 The relationship between concentration of laccase and the absorbance at 420

nm .



**Fig. S2** The absorption spectrums of decoloured BBKN-R solutions by free laccase (a) and immobilized laccase (b) for different periods of time.