

Supplementary information

*Yanxiong Pan,^{a,b} Weicai Wang,^{a,b} Chao Peng,^a Kai Shi,^a Yunxia Luo,^a Xiangling Ji^{*a}*

^a State Key Laboratory of Polymer Physics and Chemistry, Changchun Institute of Applied Chemistry, Chinese Academy of Sciences, Changchun 130022, PR of China

^b State Key Laboratory of Polymer Physics and Chemistry, Changchun Institute of Applied Chemistry, Chinese Academy of Sciences, University of the Chinese Academy of Sciences, Changchun 130022, PR of China

E-mail: xlji@ciac.jl.cn

Telephone: 86-431-85262876

The ^1H NMR of PVF




Fig S1. ^1H NMR spectra of PVF in d^6 -DMSO

The degree of acetalization (DA) of PVF is calculated from the

formulas¹:

$$\text{DA} = \frac{A_a}{A_b + A_c} \times 100\%$$

or

$$= \frac{A_a}{A_a + A_{\text{OH}}} \times 100\%$$

Here, A_a , A_b , A_c and A_{OH} is the integral area of the corresponding signal in Fig S1.

1. I. Pollers, P. Adriaensens, R. Carleer, D. Vanderzande and J. Gelan, *Macromolecules*, 1996, **29**, 5875-5881.