

Table 4. Thermal stability factors of the cured PSHG systems and PSDG systems

Sample code	T _{-5%} (°C)	T _{max1} (°C)	T _{max2} (°C)	Solid residue at 600 °C (%)
EG	332.07	347.04	377.02	4.47
PSHG2	329.31	346.85	361.99	8.64
PSHG4	316.87	/	351.33	13.17
PSDG2	328.88	/	344.89	18.44
PSDG4	323.16	/	351.29	33.54