

Supporting Information

Reaction induced phase separation in thermosetting/thermosetting blends: Effects of imidazole content on the phase separation of benzoxazine/epoxy blends

*Pei Zhao††, Qian Zhou†, Yu Yuan Deng†, Rong Qi Zhu†, Yi Gu†**

College of Polymer Sciences and Engineering, State Key Laboratory of Polymer
Materials Engineering, Sichuan University, Chengdu 610065, P. R. China

Table S1. The peak temperature (° C) of BZ/ER/MZ blends with different content of

β	MZ					
	3 wt%		8 wt%		12 wt%	
	Peak 2	Peak 3	Peak 2	Peak 3	Peak 2	Peak 3
5°C/min	153.5	195.6	138.9	185.9	129.4	179.4
10°C/min	166.9	205.4	151.3	197.1	141.6	190.4
15°C/min	175.3	212.1	162.3	205.9	151.6	197.4
20°C/min	180.4	220.0	167.7	208.5	157.1	202.4




Figure S1. The Ozawa plot of $\ln\beta$ vs. $1/T$ for fitted Peak2 and Peak3 of BZ/ER/MZ blends with different content of MZ: (a) 3wt%, (b) 8wt% and (c) 12wt%.